

Native

8x48 Color Body Porcelain



04NATPOP848



04NATWHI848



04NATBIR848



04NATPIN848



04NATCHE848



04NATTEA848



Tile: 8x48

Mosaic: N/A

Trim: N/A

For more information
and images:



Native

Color Body Porcelain



Technical Characteristics

Specs	Test Method	Industry Standard	Test Result	
Water Absorption	ASTM C373	≤ 0.5%	≤ 0.4%	
Surface Wear Resistance	ANSI A137.1	Surface wear resistance properties of glazed vitreous and porcelain tile.	All Commercial / Residential	
Chemical Resistance	ASTM C650	No tile sample shows visible defects after continuous contact with a variety of chemicals for 24 hours.	Not Affected	
DCOF (Wet)	ANSI A326.3	≥ 0.42	≥ 0.42	
Stain Resistance	ASTM C1378	Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures.	Not Affected	
Breaking Strength	ASTM C648	≥ 250 lbf	≥ 300 lbf (8 mm); ≥ 400 lbf (10 mm)	
Freeze Resistance	ASTM C1026	No tile sample shows visible defects after repeated processes of freezing and thawing.	Resistant	
Warpage Edge	ASTM C485	± 0.40% or ± 0.05 in (± 1.8 mm)	± 0.40%	Rectified
			± 0.50%	Calibrated
Warpage Diagonal	ASTM C485	± 0.40% or ± 0.07 in (± 1.8 mm)	± 0.40%	Rectified
			± 0.50%	Calibrated
Wedging	ASTM C502	± 0.25% or ± 0.03 in (± 0.8 mm)	± 0.25%	Rectified
			± 0.50%	Calibrated
Thickness	ASTM C499	Range: ± 0.04 in	≤ 0.04 in	
Recycled Content		As reported	Pre-Consumer	

Nominal Size	Actual Size	Thickness	Finish	Rectified
8" x 48"	7.75" x 47.75"	8 mm	Matte	-

All tiles have an allowance for variations in size. All of our tiles are produced with ASTM and ANSI standards. When working with a product that is baked in a kiln, variation in size is a natural part of the process.

Installation Note: The TCNA recommends rectangular shape tile be installed with maximum of 33% offset in order to resolve any possible lippage from one tile to the next.