

# Net Zero

12x24 Color Body Porcelain

mosaic   
Products. Design. Solutions.



04NETIVO1224



04NETGRA1224



04NETBEI1224



1x3 Mosaic



2x2 Mosaic



04NETLAV1224



04NETARD1224



Tile: 12x24 - 24x24 - 32x32

Mosaic: 1x3 - 2x2

Trim: 3x24 Bullnose - 6x12 Cove Base

For more information  
and images:



# Net Zero

## Color Body Porcelain



### Technical Characteristics

| Specs                    | Test Method | Industry Standard   | Test Result                         |                   |
|--------------------------|-------------|---|-------------------------------------|-------------------|
| Water Absorption         | ASTM C373   | ≤ 0.5%  | ≤ 0.5%                              |                   |
| Surface Wear Resistance  | ANSI A137.1 | Surface wear resistance properties of glazed vitreous and porcelain tile.                               | <b>All Commercial / Residential</b> |                   |
| Chemical Resistance      | ASTM C650   | No tile sample shows visible defects after continuous contact with a variety of chemicals for 24 hours. | <b>Not Affected</b>                 |                   |
| DCOF (Wet)               | ANSI A326.3 | Indoor ≥ 0.42   | ≥ 0.42                              |                   |
|                          |             | Outdoor > 0.55  | > 0.55                              |                   |
| Stain Resistance         | ASTM C1378  | Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures.              | <b>Not Affected</b>                 |                   |
| Breaking Strength        | ASTM C648   | ≥ 275 lbf   | ≥ 300 lbf                           |                   |
| Freeze Resistance        | ASTM C1026  | No tile sample shows visible defects after repeated processes of freezing and thawing.                  | <b>Resistant</b>                    |                   |
| Warpage Edge             | ASTM C485   | ± 0.40% or ± 0.05 in (± 1.8 mm)   | ± 0.40%                             | <b>Rectified</b>  |
|                          |             | ± 0.50% or ± 0.07 in (± 1.8 mm)   | ± 0.50%                             | <b>Calibrated</b> |
| Warpage Diagonal         | ASTM C485   | ± 0.40% or ± 0.07 in (± 1.8 mm)   | ± 0.40%                             | <b>Rectified</b>  |
|                          |             | ± 0.50% or ± 0.07 in (± 1.8 mm)   | ± 0.50%                             | <b>Calibrated</b> |
| Wedging                  | ASTM C502   | ± 0.25% or ± 0.03 in (± 0.8 mm)   | ± 0.25%                             | <b>Rectified</b>  |
|                          |             | ± 0.50% or ± 0.08 in (± 2.0 mm)   | ± 0.50%                             | <b>Calibrated</b> |
| Thickness                | ASTM C499   | Range: ± 0.04 in  | ≤ 0.04 in                           |                   |
| Length / Width Variation | ASTM C499   | ± 0.25% or ± 0.03 in (± 0.8 mm)   | ± 0.25%                             |                   |

| Nominal Size         | Actual Size     | Thickness | Finish | Rectified |
|----------------------|-----------------|-----------|--------|-----------|
| 12" x 24"            | 11.92" x 23.94" | 8 mm      | Matte  | -         |
| 24" x 24"            | 23.94" x 23.94" | 8 mm      | Matte  | -         |
| 32" x 32"            | 31.5" x 31.5"   | 8 mm      | Matte  | Yes       |
| 1" x 3" Mosaic       | 11.7" x 11.7"   | 8 mm      | Matte  | -         |
| 2" x 2" Mosaic       | 12" x 12"       | 8 mm      | Matte  | -         |
| 3" x 24" Bullnose    | 2.83" x 23.94"  | 8 mm      | Matte  | -         |
| 6" x 12" Cove Base * | 6.5" x 11.8"    | 7mm       | Matte  | -         |

\* This item is made to order. Please check with a sales representative for current lead times.

All tile is subject to variations in technical specifications and performance due to the inherent variables in the raw materials and production process. It is understood that test results on a particular product may vary slightly from tile to tile and from test to test. Test results are not guarantees of minimum or maximum thresholds of performance.