

COLORED BODY PORCELAIN TILE



Compliant with standards ANSI A137.1-2012

SIZE - THICKNESS

11^{3/4}"x23^{5/8}" - 30x60 cm
 23^{5/8}"x47^{1/4}" - 60x120 cm
 9^{7/8}"x8^{1/2}" - 25x21.6 cm
 7^{7/8}"x7^{7/8}" - 20x20 cm

FINISH

MATTE

9 mm



V2

SLIGHT VARIATION

While the colors and/or texture present on a single piece of tile will be indicative of the colors and/or texture to be expected on the other tiles, the amount of colors and/or texture on each piece may vary significantly. It is recommended that the range be viewed before selection.

FIELD TILES - Available in all colors

Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	Rectified edge
12"x24"	11 3/4" x 23 5/8"	9 mm	Matte	-
24"x48"	23 5/8" x 47 1/4"	9 mm	Matte	Yes
10"x8.5"	9 7/8" x 8 1/2"	9 mm	Matte	-
8"x8"	7 7/8" x 7 7/8"	9 mm	Matte	-

MOSAICS AND COORDINATING TRIMS - Available in all colors

Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish
Mosaic 2"x2"	11 3/4" x 11 3/4"	9 mm	Matte
Dart Mosaic 1.3"x4.2"	11 3/4" x 11 3/4"	9 mm	Matte
Apex Mosaic 1.8"x5.5"	11"x11"	9 mm	Matte
Bullnose 3"x24"	2 7/8" x 23 5/8"	9 mm	Matte
Cove Base 6"x12"	5 7/8" x 11 3/4"	8.5 mm (*)	Matte

Please refer to caliber chart for work sizes. Close joints are not recommended. (*): Cove Base thickness is 7 mm on flat top part.

PERFORMANCE & FEATURES

COVE

PROPERTY	ASTM TEST METHOD	Porcelain Tile Specification				COVE	
		Calibrated		Rectified			
		Minimum	Maximum	Minimum	Maximum		
REGULARITY CHARACTERISTICS	Nominal Size	-3.00%	3.00%	-3.00%	2.00%	Compliant	
		Caliber Range (Variation from average facial dimension of sample)	-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
		Thickness ⁽¹⁾	N/A	Range: 0.40 in (1.02 mm)	N/A	Range: 0.40 in (1.02 mm)	Compliant
	Wedging	ASTM C502	-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
	Warpage Edge	ASTM C485	-0.75% or -0.09 in (-2.3 mm) (*)	0.75% or 0.09 in (2.3 mm) (*)	-0.40% or -0.05 in (-1.3 mm) ⁽²⁾ or -1.8 mm ⁽³⁾ (*)	0.40% or 0.05 in (1.3 mm) ⁽²⁾ or 1.8 mm ⁽³⁾ (*)	Compliant
	Warpage Diagonal		-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.40% or -0.07 in (-1.8 mm) (*)	0.40% or 0.07 in (1.8 mm) (*)	Compliant
All Porcelain Tiles							
STRUCTURAL CHARACTERISTICS	Water Absorption	ASTM C373	≤ 0.5%		≤ 0.5%		
BULK MECHANICAL CHARACTERISTICS	Breaking Strength	ASTM C648	Average ≥ 250 lbf. (1.11 kN) Individual ≥ 225 lbf. (1.00 kN)		≥ 350 lbf. avg		
PHYSICAL PROPERTIES	Bond Strength	ASTM C482	≥ 50 psi (0.34 Mpa)		≥ 100 psi		
THERMAL AND IGROMETRIC CHARACTERISTICS	Resistance to Freeze/Thaw Cycling	ASTM C1026	As Reported		Resistant		
CHEMICAL CHARACTERISTICS	Chemical Resistance	ASTM C650	As Reported		Unaffected		
	Stain Resistance	ASTM C1378	As Reported		Unaffected		
SAFETY CHARACTERISTICS	Dynamic coefficient of friction	DCOF	Requires a minimum value of 0.42 for commercial areas that are likely to be wet		> 0.42 Wet		

(*) Whichever is less
 (1) May not apply to textured surfaces or tiles with uneven back patterns.
 (2) Whichever is less, for tiles up to 24"x24" (610 mm x 610 mm).
 (3) Applies to tiles larger than 24"x24" (610 mm x 610 mm).

The Health Product Declaration® logo is a registered trademark of HPD Collaborative.



Atlas Concorde reserves the right to modify any product without notice and will not be liable for any direct or indirect damage resulting from such modifications. Colors and optical features of the materials illustrated in this catalogue are to be regarded as mere indications. For information and details relating to codes, packaging and weight it is recommended to refer to the latest pricelist.

© Copyright Atlas Concorde USA, Inc. 2019
 The reproduction of the work, fully or in part, is strictly forbidden.