



Retro Mosaics

Porcelain


mosaic 
Products. Design. Solutions.



46METWHI2RM 



46METGRA2RM 




46METBLA2RM 




46CARCAR2H 



88U2722M 





46METWHI34PG 




88HEXWHI1MI 





88HEXWHI2MI 



88BASWHIBLA12M 




88HEXWHIBLA1M 




88HEXBLA1M 



88HEXBLA2M-MI 




88HEXGRA2M 

For more information
and images:



Retro Mosaics

Porcelain



Technical Characteristics

Test Item	Test Method	Test Result	Test Result - Square	Test Result - CAR Hex / Penny / Rhombus
Water Absorption	ASTM C373	≤ 0.5%	≤ 0.5%	≤ 0.5%
Breaking Strength	ASTM C648	Min. 290	Min. 150	-
Scratch Hardness	MOH'S	3	6	3
Chemical Resistance	ASTM C650	Unaffected	Unaffected	Resistant
Frost Resistance	ASTM C1026	Resistant	Resistant	Resistant
Minimum Bond Strength (PSI)	ASTM C482	165	≥ 50	-
Dynamic Coefficient of Friction (DCOF)	ASTM C1028	≤ 0.32 (Basket); ≤ 0.30 (Hex 1"); ≤ 0.40 (Hex 2")	≥ 0.42	N/A Penny; 0.31 (Hex / Rhombus)
Facial Dimensions	ASTM C499	Pass	Pass	-
Range of Thickness	ASTM C499	Pass	Pass	-
Warpage	ASTM C485	Pass	Pass	-
Wedging	ASTM C502	Pass	Pass	-

Nominal Size	Actual Size	Thickness	Finish
3/4" Penny	11.5" x 9.75" Sheet	5.3 mm	Glossy
1" Hex	11.81" x 11.81" Sheet	5.4 mm	Matte
2" Hex	11.81" x 11.81" Sheet	6 mm	Matte
2" CAR Hex	11.125" x 12.625" Sheet	0.25"	Matte
2" Rhombus	10.5" x 12.125" Sheet	0.25"	Matte
2" x 2" Square	11.81" x 11.81" Sheet	6 mm	Matte
12" x 12" Basketweave	11.81" x 11.81" Sheet	6 mm	Matte



For your convenience, select products are stocked in our Central Service Center.

mosaic 
Products. Design. Solutions.